

DURETE BRINELL ET CHARGE DE RUPTURE

Ø DE L'EMPREINTE mm	DURETE BRINELL HB	RESISTANCE ACIERS RECUITS kg/mm 2	RESISTANCE ACIERS TREMPES ET REVENUS kg/mm2	Ø DE L'EMPREINTE mm	DURETE BRINELL HB	RESISTANCE ACIERS RECUITS kg/mm 2	RESISTANCE ACIERS TREMPES ET REVENUS kg/mm2
2.20	780		277.0	4.15	212	72.3	75.1
2.25	745		265.0	4.20	207	70.4	73.3
2.30	712		253.0	4.25	201	68.8	71.5
2.35	682		243.0	4.30	197	67.0	69.7
2.40	653		233.0	4.35	192	65.3	68.0
2.45	627		223.0	4.40	187	64.0	66.5
2.50	601		214.0	4.45	183	62.6	65.1
2.55	578		205.0	4.50	179	61.2	63.7
2.60	555		197.5	4.55	174	59.8	62.2
2.65	534		190.0	4.60	170	58.5	60.8
2.70	514		183.5	4.65	167	57.1	59.4
2.75	495		176.5	4.70	163	55.7	58.0
2.80	477		170.0	4.75	159	54.3	56.6
2.85	461		164.0	4.80	156	53.0	55.2
2.90	444		158.0	4.85	152	51.9	54.0
2.95	429		152.5	4.90	149	50.9	53.0
3.00	415		147.5	4.95	146	49.9	52.0
3.05	401		142.5	5.00	143	48.8	50.8
3.10	388		138.0	5.05	140	47.8	49.9
3.15	375		133.5	5.10	137	46.8	48.7
3.20	363		129.0	5.15	134	45.8	47.7
3.25	352		125.5	5.20	131	44.8	46.6
3.30	341		121.5	5.25	128	43.8	45.6
3.35	331		117.5	5.30	126	42.8	44.6
3.40	321	110.0	114.0	5.35	123	41.9	43.6
3.45	311	106.5	110.5	5.40	121	41.1	42.8
3.50	302	103.0	107.0	5.45	118	40.3	42.0
3.55	293	100.0	104.5	5.50	116	39.7	41.3
3.60	285	97.5	101.5	5.55	114	39.0	40.6
3.65	277	94.5	98.5	5.60	111	38.3	39.9
3.70	269	92.0	95.5	5.65	109	37.6	
3.75	262	89.5	93.3	5.70	107	36.9	
3.80	255	87.0	90.7	5.75	105	36.2	
3.85	248	84.8	88.3	5.80	103	35.4	
3.90	241	82.3	85.7	5.85	101	34.9	
3.95	235	80.3	83.7	5.90	99	34.2	
4.00	229	78.3	81.5	5.95	97	33.5	
4.05	223	76.3	79.3	6.00	95	32.8	
4.10	217	74.3	77.3				

LES RESISTANCES A LA RUPTURE NE SONT DONNEES QU'APPROXIMATIVEMENT

Stokvis
BRANCHE BIENS INDUSTRIELS DE CONSOMMATION

R.S. STOKVIS ET FILS, S.A.
services commerciaux : 27, rue Lenine - 94 - Ivry-sur-Seine
téléphone : 672-51-39 - télex : 25.864 Stokpar Ivry
siège social : 20-22, rue des Petits-Hôtels - 75 - Paris 10^e